



## PRODUCT DATA SHEET

### TT-E-515A LUSTERLESS ALKYD ENAMEL PTI SPECIALTY SERIES

#### DESCRIPTION

**TT-E-515A** covers one type and one grade of a lusterless fast air drying enamel. This system is intended for use on military equipment for glare reduction and/or camouflage purposes.

#### COLORS

This coating can be provided in every flat or semi gloss color from the 595C FED STD. Custom colors are NOT available.

#### COATING PROPERTIES & CHARACTERISTICS

Specification	TT-E-515A
Recommended Primer(s)	PT-522
Reducer	PT-1022X66
Weight per gallon	8 lbs/gal $\pm$ 0.3

#### SHELF LIFE

Shelf life is only applicable for materials stored in unopened and undamaged original factory filled containers. 1 year when stored between 50°-85° Fahrenheit.

#### CLEANING

All parts must be chemically or mechanically cleaned, film free, by an industry recognized cleaning specification or method.

#### MIXING INSTRUCTIONS

For thinning, **PT-1022X66** reducer should be used. If **PT-1022X66** thinner is not available use Mineral Spirits. For spraying thin 4 parts paint to 1 part thinner.

#### APPLICATION

This product can be applied using brush, dripping, conventional air spray equipment or HVLP Spray system. Please consult with a PTI representative for specific equipment recommendations and settings.

1. Make sure pots, guns, and lines are purged and cleaned.
2. HVLP Spray Pressure: 7-10psi. Conventional Spray Equipment 15-30 psi
3. Always air-blow and tack wipe the surfaces to be painted. Parts should be grounded to prevent static.
4. Best application results: apply 2 coats: 1 fog/tack coat & 1 full coats from 0.75 – 1 mil thickness.
5. Allow 20-30 minutes to pass before applying additional coats.



## PRODUCT DATA SHEET

---

NOTE: Application of PTI products requires the use of all OSHA approved safety equipment, including proper ventilation. Additionally, PTI products require the recommended temperature/humidity conditions and film thickness ranges for optimal performance. The material, hangar, and aircraft skin temperatures should be no lower than 75° F / 25° C before, during and after application.

### DRYING & CURING SCHEDULE

---

**Air Dry Times** (75°F / 25°C and 50% Relative Humidity)

- Set to touch 2 hours.
- Dry Hard 8 hours
- Full Hardness 72 hours

### EQUIPMENT CLEANUP

---

Use clean Acetone, IPA, or PT-1070. Do not allow material to dry or cure inside any equipment.

### HEALTH, SAFETY, & STORAGE REQUIREMENTS

---

Refer to each individual material SDS (Safety Data Sheet) for specific requirements on the health, safety, storage and handling requirements. Follow all local, state, and national regulations during surface preparation, material application and cleanup.

### PRODUCT INFORMATION & DISCLAIMER

---

Product Data Sheets are periodically updated to reflect new information. It is important to use the latest and most recent revision for the product being used. The foregoing information is accurate to the best of our knowledge. However, due to differences in customer handling, use and method of application which are not known and are beyond our control, Products Techniques, Inc. makes no warranties as to the end result.