PolyKick

Product: PolyKick

Typical Uses:

PTI **PolyKick** is formulated to accelerate the cure times for PTI's polyurethane topcoats.

Application

At 1% by weight added to admixed material:

Tack free: 1 hour Dry hard: 1.5 hours Material jelled: 2.5 hours

At 5% by weight added to admixed material:

Tack free: 20 minutes
Dry hard: 30 minutes
Material jelled: 45 minutes

The above times are approximate. This schedule will vary depending on temperature, humidity, and climate.

Do not add more than 5%. Addition of more than 5% may adversely affect the quality of the cured topcoat.

Refer to MSDS for all health and safety precautions.

NOTE: The foregoing is accurate to the best of our knowledge. However, conditions of use, storage and handling do affect the performance of the coating. Since these factors are beyond our control we do not guarantee individual results. For satisfactory results, PTI reducers must be used as recommended.

