

## PRODUCT DATA SHEET

### PT-110 ACRYLIC LACQUER TOPCOAT PTI LACQUER SERIES

#### DESCRIPTION

**PT-110** is a general purpose high performance, single component acrylic lacquer topcoat designed for interior or exterior use on metal surfaces. PT-110 meets and exceeds **MIL-L-81352A & BELL SPEC 299-947-069** is an excellent coating to apply over both metal and composite substrates. This product is available in bulk and aerosol cans.

#### COLORS

This coating can be provided in **any color & gloss range** as designated by the Federal Standard 595C. Custom colors are also available.

#### COATING PROPERTIES & CHARACTERISTICS

Flash Point	76°F
Reducer	PT-1002 or PT-1003 TYIII
Primer	PT-562 & PT-500
Recommended Dry Film Thickness	1 mil
Weight (lbs per gallon)	9 to 11 lbs
Theoretical Coverage	300 sq. ft./gallon

#### SHELF LIFE

Shelf life is only applicable for materials stored in unopened and undamaged original factory filled containers. 1 year when stored between 50°-85° Fahrenheit.

#### MIXING INSTRUCTIONS

Shake component A in a paint shaker for 5 – 10 minutes for optimal results.

**Reduce:** Use PT-1002 or PT-1003 TYIII to thin this product.

- **If Spraying:** Thin 1part paint to 1.5 parts thinner by volume.
- **If Brushing:** Thin 2 parts paint to 1 part thinner or as necessary.

#### APPLICATION

This product can be applied by brushing, rolling, conventional air spray equipment or a HVLP spray system. Please consult with a PTI representative for specific equipment recommendations and settings.

1. Make sure pots, guns, and lines are purged and cleaned.
2. Mix both paint and reducer thoroughly and filter/strain before spray application.  
**NOTE:** It is not recommended to strain flat/matte coatings.
3. HVLP Spray Pressure: 7-10psi. Conventional spray pressure 15-30psi
4. Always air-blow and tack wipe the surfaces to be painted. Aircraft should be grounded to prevent static.

---

## PRODUCT DATA SHEET

---

5. Best application results: apply 2 coats: 1 fog/tack coat & 1 full coat from 0.6 – 1 mil thickness.
6. Do not allow more than 12 hours to pass before applying the second coat.
7. Recommended Dry Film Thickness is 1-1.2 mils. Some colors may require thicker films to achieve hiding.

NOTE: Application of PTI products requires the use of all OSHA approved safety equipment, including proper ventilation. Additionally, PTI products require the recommended temperature/humidity conditions and film thickness ranges for optimal performance. The material, hangar, and aircraft skin temperatures should be no lower than 75° F / 25° C before, during and after application.

---

### DRYING & CURING SCHEDULE

---

Dry times are based on the dry film thickness between 1-1.2 mils (25-50 microns).

**Air Dry Times** (75°F / 25°C and 50% Relative Humidity)

Dries hard in 10 minutes; full cure in 72 hours.

**Force Cure:** Air dry for 10 minutes, then bake for no longer than 1 hour at 120°F

---

### EQUIPMENT CLEANUP

---

Use the recommended reducers, IPA or Acetone. Do not allow material to dry or cure inside any equipment.

---

### HEALTH, SAFETY, & STORAGE REQUIREMENTS

---

Refer to each individual material SDS (Safety Data Sheet) for specific requirements on the health, safety, storage and handling requirements. Follow all local, state, and national regulations during surface preparation, material application and cleanup.

---

### PRODUCT INFORMATION & DISCLAIMER

---

Product Data Sheets are periodically updated to reflect new information. It is important to use the latest and most recent revision for the product being used. The foregoing information is accurate to the best of our knowledge. However, due to differences in customer handling, use and method of application which are not known and are beyond our control, Products Techniques, Inc. makes no warranties as to the end result.