



IGS3760

Two-Component Insulating Glass Sealant

Product Description

IGS3760 adhesive silicone is an optimized, high-modulus, neutral curing sealant for edge seal applications for gas and air filled structural and non-structural insulating glass units. IGS3760 offers variable work life to accommodate scheduling and production needs.

Key Features and Typical Benefits

- **High Modulus**—Minimizes movement of the primary PIB seal to better retain gas inside and keep moisture out of the insulating glass unit.
- **High Elastic Recovery**—Helps to maintain the original edge design dimensions of the insulating glass unit.
- **Fast Cure**—May allow for shipping of fabricated insulating glass units within hours of completion without silicone transfer or glass shifting.
- **Compatibility**—Compatible with GE structural and weather sealing silicones as well as many commonly used accessories in the glass and glazing trade.
- **Non-flammable**—Does not require special handling or storage associated with flammable materials.

Potential Applications

- **Structural Glazing**—May be utilized as the secondary sealant for insulating glass units with or without inserts in the edge seal fabricated for structural glazing applications.
- **Silicone Durability**—Cured silicone rubber exhibits excellent long term resistance to natural weathering including: extreme temperatures, ultraviolet radiation, rain and snow, with negligible change in elasticity.
- **Adhesive**—Attains strong bonds to hard coated and uncoated glass as well as to many conventional and warm edge types of spacers without a primer.

Note:

IGS3760 silicone should only be used in the fabrication of insulating glass where the dual seal method of fabrication is used. The moisture vapor transmission rate of silicone sealants is sufficiently high as to preclude their use in the fabrication of single seal insulating glass units.

- Silicone setting blocks are recommended for direct contact with IGS3760 silicone. Avoid using non-silicone materials (i.e., EPDM, Neoprene) as they could degrade or discolor the secondary seal over time. Compatibility testing is recommended on all materials that are to be in direct contact with IGS3760 silicone.
- Avoid IGS3760 to be in contact with or exposed to sealants that evolve acetic acid cure byproduct.
- Not recommended for water immersion applications.

Packaging

IGS3760 silicone is currently comprised of the following:

Base Options:

- IGS3760A—White paste in 55 gallon (200 liter) drums filled to a weight of 620 Lbs. (281.48 kg) with polyethylene liner.

Catalyst Options:

- IGS3760B Black—Black paste, mixes and cures to a black silicone rubber. Available in 5 gallon (18.9 liter) pails filled to 40 Lbs. (18.16 kg) and 55 gallon (208 liter) drums filled to 450 Lbs. (204 kg).

Colors

IGS3760 silicone is currently available in black:

Black: IGS3760A mixed with IGS3760B Black



Black

Uncured Product Storage

Base should be stored in sealed containers in a dry area at temperatures at or below 80°F (27°C).

Catalyst should be stored in sealed containers in a dry area at temperatures at or below 70°F (21°C).

Keep both base and catalyst containers out of direct sunlight.



Typical Physical Properties

Typical physical property values of IGS3760 two-component insulating glass silicone as supplied and cured are set forth in the tables below.

Typical Properties—Uncured⁽¹⁾

Uncured Properties	Base	IGS3760A
Color	Grey/White	Thixotropic Paste
Specific Gravity	1.5 Kg/l	–
Shelf Life	18 months ⁽²⁾	–
Uncured Properties	Catalyst	IGS3760B Black
Color	Black	Thixotropic Paste
Specific Gravity	1.11 Kg/l	–
Shelf Life	12 months ⁽²⁾	–

Mixed Compound Properties

IGS3760A+IGS3760B Black		
Color	Black / Grey	Thixotropic Paste
Specific Gravity	1.47 Kg/l	Mixed at 12.5:1 weight
Mix Ratio Range	8:1 to 11:1	By volume
Snap Time	20-85 minutes	Depends on ratio, temperature & RH
Tack Free Time	2X snap time	Depends on ratio, temperature & RH
Consistency/Sag	<0.05"	Non-sagging

Cured Properties⁽³⁾

Full Cure at Standard Laboratory Conditions @ 12.5:1 weight ratio IGS3760A+IGS3760B Black		
Color	Black / Grey	–
Hardness Points (type A indenter)	55	ASTM D2240
Ult. Tensile Strength	305 psi (2.1 MPa)	ASTM D412
Ult. Elongation	222%	
Tear Strength	37 ppi (6.81 N/mm)	ASTM D624, die B
Shear Strength	130 psi (0.90 MPa)	ASTM C961
Tensile Strength	1.0 MPa (145 psi)	ISO 8339
Elongation at break	60%	
Modulus @ 25%	0.7 MPa (101 psi)	
Tensile Strength	165 psi (1.12 MPa)	ASTM C1135
Elongation at break	46%	
Modulus @ 10%	64 psi (0.44 MPa)	
Modulus @ 25%	125 psi (0.86 MPa)	
Accelerated Weathering, 5000 hours	Excellent, no degradation	ASTM C1369
Heat Resistance	300°F (149°C)	–
Design stress in tension	0.15 Mpa	ETAG 002
Elastic modulus in tension or compression	2.60 Mpa	ETAG 002
Resistance to tearing	category 1	ETAG 002
Moisture vapor transmission rate	23.4 g/m ²	EN1279-4
Gas permeability	0.924 g/m ² h	EN1279-4

(1) Typical properties are average data and are not to be used as or to develop specifications.

(2) When properly stored; see section on storage.


(3) Typical value, actual value may vary.

Installation

Refer to current specifications, installation guidelines and details for application instructions.

IGS3760 Volume to Weight Ratio Correlation

Volume	Weight
8:1	11.5:1
9:1	13.0:1
10:1	14.4:1
11:1	15.9:1



Applicable Standards

IGS3760 Insulating Glass Silicone meets or exceeds the requirements of the following standards and specifications:

- American Society for Testing and Materials
 - C1369 Standard Specification for Secondary Edge Sealant for Structurally Glazed Insulating Glass Units
 - E2190-10 Standard Specification for Insulating Glass Unit Performance and Evaluation
- European Organization for Technical Approvals
 - European Assessment Document ETAG002
- European Committee for Standardization
 - EN1279 Glass in Buildings - Insulating Glass Units -
 - Part 2: Long term test method and requirements for moisture penetration
 - Part 3: Long term test method and requirements for gas leakage rate and for gas concentration tolerances
 - Part 4: Methods of test for the physical attributes of edge seals
- Standardization Administration of China
 - GB24266 Secondary edge silicone sealant for structurally glazed insulating glass units



Technical Services

For additional technical information, please contact your local customer service center. (See Customer Service Centers section herein for contact information.) Any technical advice furnished by Momentive Performance Materials (MPM) or any representative of MPM concerning any use or application of any MPM product is believed to be reliable, but MPM makes no warranty, expressed or implied, of suitability for use in any application for which such advice is furnished.

Limitations

Customers must evaluate MPM products and make their own determination as to fitness of use in their particular applications.

Patent Status

Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute the permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of the patent.

Product Safety, Handling and Storage

Customers considering the use of this product should review the latest Safety Data Sheet and label for product safety information, handling instructions, personal protective equipment if necessary, and any special storage conditions required. Safety Data Sheets are available at siliconeforbuilding.com or, upon request, from any MPM representative. Use of other materials in conjunction with MPM sealants products (for example, primers) may require additional precautions. Please review and follow the safety information provided by the manufacturer of such other materials.



Customer Service Centers

Americas	+1 800 295 2392 +1 704 805 6946 Email: commercial.services@momentive.com
Europe, Middle East, Africa, and India	+00 800 4321 1000 +40 212 044229 Email: 4information.eu@momentive.com
Asia Pacific	Japan 0120 975 400 +81 276 20 6182 China +800 820 0202 +86 21 3860 4892 All APAC +60 3 9206 1543 Email: 4information.ap@momentive.com
Visit us at www.siliconeforbuilding.com	

THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC. AND ITS SUBSIDIARIES AND AFFILIATES (COLLECTIVELY "SUPPLIER"), ARE SOLD SUBJECT TO SUPPLIER'S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING ITS PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. EXCEPT AS PROVIDED IN SUPPLIER'S STANDARD CONDITIONS OF SALE, SUPPLIER AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBE HEREIN. Each user bears full responsibility for making its own determination as to the suitability of Supplier's materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Supplier's products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Supplier's standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Supplier. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Supplier covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.

Before purchasing or using any Momentive products, please visit www.siliconeforbuilding.com/legaldisclaimer to view our full product and sales disclaimer.

GE is a registered trademark of General Electric Company and is used under license by Momentive Performance Materials Inc.

Copyright 2017-2019 Momentive Performance Materials Inc. All rights reserved.

siliconeforbuilding.com