



Enduris* Asphalt Bleed Blocker

Bleed Resistant Basecoat for Enduris 3500 Silicone Topcoat

Product Description

GE** Enduris Asphalt Bleed Blocker is a long lasting, breathable, and flexible barrier coating used for prevention of bleed from asphaltic materials and asphalt-based surfaces.

Key Features and Typical Benefits

- **Versatility**—Single component acrylic polymer resin basecoat for spray, brush or roller application
- **Bleed Resistance**—Formulated with special materials to block the bleed-through of asphaltic components that can discolor topcoats
- **Excellent Adhesion**—Offers exceptional adhesion to asphaltic surfaces
- **Breathability**—Asphalt Bleed Blocker is part of a breathable coating system that allows trapped moisture to escape.
- **Color Contrast**—Color is light yellow as installed and darkens as it cures, allowing enhanced visual confirmation for application of the basecoat and also a white topcoat.

Potential Applications

- A barrier coating for use on surfaces such BUR or Modified Bitumen. (Check with your Momentive Performance Materials (MPM)/GE Silicones representative for compatibility with other substrates.)

Note: GE Enduris Asphalt Bleed Blocker should not be considered for use on wet substrates or when inclement weather is imminent. This product is not intended as a thermal barrier.

Packaging

Asphalt Bleed Blocker is currently available in the following configurations:

- 5 gallon pail (18.9 liters), 55 pounds (24.9 kg)
- 55 gallon drum (208.2 liters), 611 pounds (276.9 kg)

Colors

Asphalt Bleed Blocker is available as a stock color in light yellow.

Limitations

Enduris Asphalt Bleed Blocker should not be considered for:

- Unprepared surfaces including but not limited to those that are wet, dusty, oily, mildewed, heavily chalked, blistered, or structurally unsound.
- Cold storage roofing application without vapor barrier or cryogenic tank applications.
- Use on areas that are exposed to water for extended periods of time.
- **Surfaces where adhesion has not been verified by testing.**

*Enduris is a trademark of Momentive Performance Materials Inc.

**GE is a registered trademark of General Electric Company and is used under license by Momentive Performance Materials, Inc.



Typical Physical Properties

Typical physical property values of Enduris* Asphalt Bleed Blocker as supplied and cured are set forth in the tables below.

Typical Properties⁽¹⁾

Property	Test Method	Result
Volume Solids	ASTM D 2697	46.0
Tensile Strength	ASTM D 2370	250 psi
Elongation	ASTM D 2370	250%
VOC	EPA Method 24	< 50 g Liter
Viscosity		30,000 cps
Weight per gallon		11.1 lbs (5.1 kg) per gallon
Flashpoint		Non Flammable
Shelf Life		12 months
Clean Up		Soap and water

(1) Typical properties are average data and are not to be used as or to develop specifications.

Typical Dry / Cure Times⁽¹⁾

Yield 1 gal to 100 square feet (1 gal to 9.29 square meter)	7.4 dry mils
Dry Time 75°F (24°C)	2-4 hours

(1) Typical properties are average data and are not to be used as or to develop specifications.

General Considerations for Use

Environmental Conditions

This product cures by water evaporation only. Product must not be applied when the ambient temperature is below 45°F (7°C) or if there is any possibility it could fall below 32°F (0°C) within 24 hours of application. Application is not recommended if rain or dew is likely to occur before product dries. In high humidity conditions, late afternoon applications should be avoided as overnight dew formation on uncured surface can cause coating wash-off. On marginal days, multiple applications of thin coats can help ensure proper drying before rain or overnight freezes.

Surface Preparation

General: Surfaces to be coated should be dry, free of dust, dirt, oil, loose granules, gravel, peeling coating and other foreign matter. All wet insulation should be removed and replaced with like compatible materials.

For optimal results, power wash all surfaces with a minimum of 2000 psi using a wide fan tip. All necessary precautions should be taken to avoid damage to the roof system. Mildew should be treated with a bleach solution (1 part Bleach, 2 parts water) and rinsed thoroughly. Patch and repair cracks or holes with appropriate sealants or caulking materials.

Application

Mix well before using.

This product may be brushed rolled or sprayed on a clean, dry surface.

- Ambient temperatures should be above 40°F (5°C) and rising, with relative humidity below 90% and no threat of rain for 48 hours. Coating substrate should be warmer than 40°F (5°C) and not over 100°F (38°C). Before applying additional coat, the previous coat must be completely cured and dry.
- If any contamination is present on the cured surface, it must be washed and completely dry before application of subsequent coats.

Coverage Rate

Apply Asphalt Bleed Blocker at the minimum rate of 1.0 gallon per 100 square feet (9.3 square meters) (16 wet mils). Surface texture and wind will affect applied mil thickness. For areas where asphaltic materials are less than 30 days old, such as repairs and patches, allow the Asphalt Bleed Blocker to cure for 2 to 24 hours depending on temperature and wind, then install a second application at a rate of 1.0 gallon per 100 square feet (9.3 square meters) (16 wet mils). Once completely dry, Asphalt Bleed Blocker can be top-coated with Enduris 3500 Series Silicone Coating.

Uncured Product Storage

Asphalt Bleed Blocker containers should be tightly sealed when not in use, and stored below 90°F (32°C). Keep from freezing.

Limitations

Customers must evaluate Momentive Performance Materials products and make their own determination as to fitness of use in their particular applications.

Patent Status

Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute a permission, inducement, or recommendation to practice any invention covered by any patent, without authority from the owner of the patent.

Product Safety, Handling and Storage

Customers should review the latest Safety Data Sheet (SDS) and label for product safety information, safe handling instructions, personal protective equipment if necessary, and any special storage conditions required for safety. Safety Data Sheets are available at www.ge.com/silicones or, upon request, from any MPM representative. Use of other materials in conjunction with MPM products (for example, primers) may require additional precautions. Please review and follow the safety information provided by the manufacturer of such other materials.



Customer Service Centers

Americas	+1 800 295 2392 +1 704 805 6946 Email: commercial.services@momentive.com
Europe, Middle East, Africa, and India	+00 800 4321 1000 +40 212 044229 Email: 4information.eu@momentive.com
Asia Pacific	Japan 0120 975 400 +81 276 20 6182 China +800 820 0202 +86 21 3860 4892 All APAC +60 3 9206 1543 Email: 4information.ap@momentive.com
Visit us at www.ge.com/silicones	

DISCLAIMER

THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC. AND ITS SUBSIDIARIES AND AFFILIATES (COLLECTIVELY "SUPPLIER"), ARE SOLD SUBJECT TO SUPPLIER'S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING ITS PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. EXCEPT AS PROVIDED IN SUPPLIER'S STANDARD CONDITIONS OF SALE, SUPPLIER AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN. Each user bears full responsibility for making its own determination as to the suitability of Supplier's materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Supplier's products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Supplier's standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Supplier. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Supplier covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.

*Enduris is a trademark of Momentive Performance Materials Inc.

**GE is a registered trademark of General Electric Company and is used under license by Momentive Performance Materials Inc.

Copyright 2020 Momentive Performance Materials Inc. All rights reserved.

siliconeforbuilding